DATASHEET

ServoMulti S 105

Self-leveling compound

- self-leveling
- 1 - 5 mm layer thickness
- for indoor use
- pumpable



PRODUCT DESCRIPTION

Cement-bound, plasticised, self-leveling compound with good spreading properties for leveling of substrates. Ready for covering up to 5 mm layer thickness. Also suitable for asphalt screeds with a hardness class of IC 10, in layers up to 5 mm thick. **ServoMulti S 105** is suitable as a substrate for laying elastic, textile floor coverings as well ceramic tiles.
ServoMulti S 105 cannot be used as a final floor or in wet rooms.

SUBSTRATE PREPARATION

The substrate must be inspected and ready for installation in accordance with the respective regulations of the individual countries as well as the current state of technology.

Depending on the type of substrate and its subsequent use, prime with **Okatmos® EG 10, Okatmos® EG 20**, **Okatmos® EG 25, Okatmos® UG 30**, **Okatmos® DSG**, **Okamul PU-V schnell**, **Okapox GF** or **Okapox SPG**. The technical data sheets for the products used must be observed. A system structure assembly must be provided.

PROCESSING

Mix **ServoMulti S 105** with drinking water at a maximum speed of 600 rpm, using an electric mixer, until there are no clumps. Leave to stand for approx. 5 minutes and then mix again. Next, apply with a smooth or notch trowel. Avoid direct sunlight and draughts during the drying period. If in doubt, create a test surface with **ServoMulti S 105.**

Kiesel Bauchemie GmbH u. Co. KG
Wolf-Hirth-Straße 2
D-73730 Esslingen
Phone: 0711 93134-0
Fax: 0711 93134-140
www.kiesel.com
Stuttgart District Court HRA 210806

CEO:
Beatrice Kiesel-Luik
Dirk Schulze

Personally liable partner::
Kiesel Verwaltungsges. mbH
Stuttgart District Court HRB 210484
Registered Office of the company:
73730 Esslingen

SPECIFICATIONS

Color	grey
Application	indoors, on floors, in dry areas
Thickness	1 - 5 mm
Suitable for chair castors (DIN EN 12529)	suitable from 1 mm layer thickness
Water demand	6,5 - 6,7 litres per 25 kg powder
Processing time*	approx. 40 minutes
Walkable*	after approx. 2 hours
Ready for installation*	after approx 24 hours
Floor heating system	suitable
EMICODE®	EC 1PLUS according to GEV
Storage	store in a dry place; can be stored for approx. 6 months

* At 68 °F (+20 °C) and 65% relative humidity. Higher temperature and low humidity decreases, lower temperature and high humidity increasesthis value respectively.

COVERAGE

consumption*	approx. 0,30722 lbs/ft^2 (ca. 1,5 kg/m^2)
coverage* per 55 lbs (25 kg) paper sack	approx. 179 ft^2

Coverage is approximate and is given for estimating purposes only. It may vary according to substrate conditions and other factors.

CLEANING

Clean tools immediately with water.

PACKAGING

Product description	Item no.	Item no.
42 x 25 kg paper sacks	80305	4015705803050

The aforementioned information, especially the proposals for processing and utilizing our product, is based on our knowledge and experience. We recommend that you carry out your own tests in every case to ensure the suitability of our products for the intended process and processing purposes because of the different materials and the working conditions which lie beyond our area of influence. No liability can be derived from this advice or from verbal advice, unless we are responsible for (criminal) intent or gross negligence in this respect.

Kiesel Bauchemie GmbH u. Co. KG
Wolf-Hirth-Straße 2
D-73730 Esslingen
Phone: 0711 93134-0
Fax: 0711 93134-140
www.kiesel.com
Stuttgart District Court HRA 210806

CEO:
Beatrice Kiesel-Luik
Dirk Schulze

Personally liable partner::
Kiesel Verwaltungsges. mbH
Stuttgart District Court HRB 210484
Registered Office of the company:
73730 Esslingen

Revised: 20.01.2023/ag

Kiesel Bauchemie GmbH u. Co. KG
Wolf-Hirth-Straße 2
D-73730 Esslingen
Phone: 0711 93134-0
Fax: 0711 93134-140
www.kiesel.com
Stuttgart District Court HRA 210806

CEO:
Beatrice Kiesel-Luik
Dirk Schulze

Personally liable partner::
Kiesel Verwaltungsges. mbH
Stuttgart District Court HRB 210484
Registered Office of the company:
73730 Esslingen